

## CHEMICAL RESISTANCE

- SPARTA-FLEX® GLOSS & LO GLOSS
- SPARTA-FLEX® PIGMENTED
- SPARTA-FLEX® PURE™



US Patents: 6.833,424 & 7,169,876

### CHEMICAL RESISTANCE DATA

Material	No Effect	Slight Effect	Not Recommended
Acetic Acid			
Acetic Acid 25%		X	
Acetone		X	
Ammonium Hydroxide: 10%	X		
Ammonia: 20%	X		
Antifreeze	X		
Brake Fluid	X		
Chlorinated Pool Water (pH 6.5)	X		
Chromic Acid		X	
Citric Acid 25%	X		
Clorox: 20%	X		
Coffee	X		
Cola	X		
Commercial Paint Remover			X
Diesel Fuel	X		
Ethyl Alcohol: 50%	X		
Formaldehyde	X		
Gasoline	X		
Hydraulic Fluid	X		
Hydrochloric Acid 20%	X		
Hydrogen Peroxide 30%		X	
Isopropanol Alcohol	X		
Jet Fuel	X		
Lactic Acid 25%	X		
Methyl Ethyl Ketone			X
Mineral Oil	X		
Mineral Spirits	X		
Motor Oil	X		
Muratic Acid: 10%	X		
Nitric Acid 5%	X		
Paint Thinner (Aliphatic Hydrocarbon)	X		
Phosphoric Acid	X		
PM Solvent		X	
Potassium Hydroxide		X	
Propylene Glycol	X		
Quadry Ammonia: 20%	X		
Skydrol B	X		
Sodium Hydroxide: 50%	X		
Sulfuric Acid: 10%	X		
Tannic Acid 20%	X		
Trisodium Phosphate 5%	X		
Vinegar	X		
Xylene		X	

\* Chemical resistance reflects patented Sparta-Flex® High Performance polyaspartic coatings following minimum cure time of 18 days.

www.hpspartacote.com